

AMENDMENTS TO THE CLAIMS

The following listing of claims replaces all prior listings of claims presented in this application.

Claim 1 (Currently Amended): A polyamide-based laminated film with a multi-layered structure including 5 or more layers, comprising (a) an aromatic polyamide layer, (b) an aliphatic polyamide layer and (c) a layer made of a mixture containing an aromatic polyamide and an aliphatic polyamide at a weight ratio of 5:95 to 20:80, said layer (c) being disposed adjacent to the layer (a) and/or the layer (b), and said film having 5 or less pinholes per 497 cm² as measured after subjecting the film to 3000 cycles of repeated flexing operation at a temperature of 23°C and a relative humidity of 50%, using a Gelboflex tester, wherein the layer (a) contains a flex/pinhole resistance modifying agent in an amount of 0.1 to 10% by weight.

Claim 2 (Original): The polyamide-based laminated film according to claim 1, wherein said film has a multi-layered structure in which the layer (b), the layer (c) and the layer (a) are sequentially laminated on each other in this order.

Claim 3 (Original): The polyamide-based laminated film according to claim 2, wherein said film has a multi-layered structure in which the layer (b), the layer (c), the layer (a), the layer (c) and the layer (b) are sequentially laminated on each other in this order.

Claim 4 (Previously Presented): The polyamide-based laminated film according to claim 1, wherein said film comprises two or more layers (c) having different compositions from each other.

Claim 5 (Canceled).

Claim 6 (Currently Amended): The polyamide-based laminated film according to claim 5, wherein the layer (c) and/or the layer (b) contain a flex/pinhole resistance modifying agent in an amount of 0.1 to 10% by weight.

Claim 7 (Previously Presented): The polyamide-based laminated film according to claim 1, wherein the film is a monoaxially or multi-axially stretched film which is stretched at a stretch ratio of 2 to 8 times in at least one direction thereof.

Claim 8 (Original): The polyamide-based laminated film according to claim 7, wherein the film is a biaxially stretched film which is stretched at a stretch ratio of 2.5 to 5 times in each of longitudinal and lateral directions thereof.

Claim 9 (Previously Presented): The polyamide-based laminated film according to claim 1, wherein the layer (a) is an aromatic polyamide layer containing the aliphatic polyamide in an amount of 0 to 5% by weight.

Claim 10 (Previously Presented): The polyamide-based laminated film according to claim 1, wherein the layer (b) is an aliphatic polyamide layer containing the aromatic polyamide in an amount of 0 to 5% by weight.

Claim 11 (Previously Presented): The polyamide-based laminated film according to claim 1, wherein at least one layer of the film is a polyamide-based resin layer containing a hindered phenol-based antioxidant in an amount of 0.01 to 0.5% by weight, and a thickness of the polyamide-based resin layer is 10% or more but less than 80% of a whole thickness of the film.

Claim 12 (Original): The polyamide-based laminated film according to claim 11, wherein the hindered phenol-based antioxidant is at least one compound selected from the group consisting of N,N'-hexamethylenebis(3,5-di-t-butyl-4-hydroxy-hydrocinnamide), 3,5-di-t-butyl-4-hydroxy-

benzylphosphonate-diethyl ester, 1,3,5-trimethyl-2,4,6-tris(3,5-di-*t*-butyl-4-hydroxy-benzyl)benzene and pentaerythrityl-tetrakis[3-(3,5-di-*t*-butyl-4-hydroxyphenyl)propionate].

Claim 13 (Previously Presented): The polyamide-based laminated film according to claim 11, wherein the polyamide-based resin layer containing the hindered phenol-based antioxidant is made of nylon-6 and/or nylon-66.

Claim 14 (Previously Presented): The polyamide-based laminated film according to claim 1, wherein in addition to the layers (a), (b) and (c), the film further comprises (d) a layer made of a saponified ethylene-vinyl acetate copolymer.

Claim 15 (New): The polyamide-based laminated film according to claim 1, wherein the layer (c) is made of a mixture containing an aromatic polyamide and an aliphatic polyamide at a weight ratio of 10:90 to 15:85.